



# vestige

## LAB PUTTY 95

Putty consistency addition silicone created to be used in dental laboratories. Final hardness 95 Shore "A".

### Description / Use

Hand mixing vinylpolysiloxane used for the realization of masks and for the laboratory applications (registration and moulding) that requires the exact reproduction of the surfaces with which it comes into contact. Moldable during its working and very rigid after setting, it maintains unaltered the information recorded in any condition of use. It can be scanned. Colour: green.

#### Standard packaging REF 1L1100

VESTIGE LAB PUTTY 95: 2x5Kg  
buckets(base+catalyst)

### Characteristics

Mixing ratio 1:1  
 Biocompatible  
  
 High final hardness  
  
 Resistant to heat, pressure and monomers  
 Dimensional stability  
  
 Easy to scan  
  
 Precise

### Advantages

Easy to dose  
 Gloves not required during the mixing phase  
 Stable and accurate during repositioning  
 Unalterable in any condition of use  
 Unaltered in time restorations, even after weeks  
 Compatible with all CAD/CAM systems  
 Better reproduction of details

TECHNICAL DATA	VESTIGE LAB PUTTY 95
Mixing ratio	1:1
Mixing time (23°C)	30"
Total working time (23°C)	2'
Setting time (23°C)	6'
Hardness	95 Shore "A"
Linear dimensional change	< 0,20%
Elastic recovery	>99,5%